

## Dymonic® 100

### High Performance, High Movement Polyurethane Sealant

#### Product Description

Dymonic® 100 is a high performance, medium-modulus, low-VOC, UV stable, non-sag polyurethane sealant. Formulated with an innovative polymer technology similar to TREMproof 250GC and Vulkem 45 SSL, Dymonic 100 is a highly versatile sealant that has a unique capability to adhere to damp or green concrete.

#### Basic Uses

Dymonic 100 is a durable, flexible, sealant that offers excellent performance in moving joints and exhibits tenacious adhesion once fully cured. Typical applications for Dymonic 100 include expansion and control joints, precast concrete panel joints, perimeter caulking (windows, door, panels), aluminum, masonry and vinyl siding.

#### Features and Benefits

Dymonic 100 can adhere to damp or green concrete and has a skin time of 2 hours with a tack-free time of 6-8 hours to significantly reduce dirt pickup. It has a movement capability of +100/-50% in typical field conditions, is low-VOC, paintable and will not crack, craze or yellow under extreme UV exposure. It is also jet fuel resistant.

Dymonic 100 is compatible with Tremco's line of Vulkem Deck Coatings, ExoAir air barrier products and the cold, fluid-applied TREMproof line of below-grade waterproofing products.

#### Availability

Dymonic 100 is immediately available from your local Tremco Sales Representative, Tremco distributor or warehouse.

#### Colors

Almond, Aluminum Stone, Anodized Aluminum, Beige, Black, Bronze, Buff, Dark Bronze, Gray, Gray Stone, Hartford Green, Ivory, Light Bronze, Limestone, Natural Clay, Off White, Precast White, Redwood Tan, Sandalwood, Stone, White

#### Packaging

10.1-oz (300ml) cartridges; 20-oz (600ml) sausages.

#### Coverage Rates

308 linear feet of joint per gallon for a 1/4 in. x 1/4 in. (6mm x 6mm) joint. For specific coverage rates that include joint size, and usage efficiencies, visit our website usage calculator at [www.tremcosealants.com](http://www.tremcosealants.com).

#### Applicable Standards

Dymonic 100 meets or exceeds the requirements of the following specifications:

- ASTM C920 Type S, Grade NS, Class 50, Use NT, T, M, A, O, I
- U.S. Federal Specification TT-S-00230C, Class A, Type II
- CAN/CGSB-19,13-M87

#### Joint Design

Dymonic 100 may be used in vertical or horizontal joints designed in accordance with accepted architectural/engineering practices. Joint width should be 4 times anticipated movement, but not less than 1/4 in. (6mm).

### TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Typical Value
Rheological Properties	ASTM C639	non-sag (NS), 0" of sag in channel
Hardness Properties	ASTM C661	40 ± 5
Weight Loss	ASTM C1246	Pass
Skin Time	ASTM C679	2-3 hr
Tack Free Time at 73.4° F (23° C) 50% RH		6-8 hr
Stain & Color Change	ASTM C510	No visible color change/No stain
Effects of Accelerated Aging	ASTM C793	Pass
Movement Capability	ASTM C719	+50%
	ASTM C719*	+100/-50%
Tensile Properties	ASTM D412	
Tensile Strength		350-450 psi
% Elongation		800-900%
Modulus at 100%		75-85 psi
Tear Strength	ASTM D624	65-75 psi
Service Range		-40° F (-40° C) to 180° F (82° C)
Application Temperature		32° F (0° C) to 100° F (38° C)
Smoke Development	ASTM E84	5
Flame Spread	ASTM E84	5


\*Modified ASTM C 719

## Joint Backing

Closed cell or reticulated polyethylene backer rod is recommended as joint backing to control sealant depth and to ensure intimate contact of sealant with joint walls when tooling. Where depth of joint will prevent the use of backer rod, an adhesive backed polyethylene tape (bond breaker tape) should be used to prevent three-sided adhesion. All backing should be dry at time of sealant application.

## Sealant dimensions

W = Sealant width, D = Sealant depth, C = Contact area.



**EXPANSION JOINTS** - The minimum width and depth of any sealant application should be 1/4 in. by 1/4 in. (6mm by 6mm). The depth (D) of sealant may be equal to the width (W) of joints that are less than 1/2 in. wide. For joints ranging from 1/2 in. to 1 in. (13mm to 25mm) wide, the sealant depth should be approximately one-half of the joint width.

The maximum depth (D) of any sealant application should be 1/2 in. (13mm). For joints that are wider than 1 in. (25mm) contact Tremco Technical Services or your local Tremco Sales Representative.

**WINDOW PERIMETERS** – For fillet beads, or angle beads around windows and doors, the sealant should exhibit a minimum surface contact area (C) of 1/4 in. (6mm) onto each substrate, with provisions for release at the heel of the angle using backer rod or bond breaker tape.

## Surface Preparations

Surfaces must be sound and clean. All release agents, existing waterproofing, dust, loose mortar, paints, or other finishes must be removed. This can be accomplished with a thorough wire brushing, grinding, sandblasting, or solvent washing, depending on the contamination.

Tremco recommends that surface temperatures be 40° F (5° C) or above at the time the sealant is applied. If sealant must be applied in temperatures below 40° F, please refer to the Tremco Guide for Applying Sealants in Cold Weather that can be found on our website at [www.tremcosealants.com](http://www.tremcosealants.com).

## Priming

Dymonic 100 typically adheres to common construction substrates without primers. However, Tremco always recommends that a mock-up or field adhesion test be performed on the actual materials being used on the job to verify the need for a primer. A description of the field adhesion test can be found in appendix X1 of ASTM C 1193, Standard Guide for Use of Joint Sealants. Where deemed necessary, use Vulkem Primer #171 on porous substrates and TREMprime Non-Porous Primer for metals or plastics.

## Application

Dymonic 100 is easy to apply with conventional caulking equipment. Ensure that the backer rod is friction fitted properly and any primers have been applied. Fill the joint completely with a proper width-to-depth ratio, and tool to ensure intimate contact of sealant with joint walls. Dry tooling is always preferred, although compatible wetting agents can be used in limited amounts to slick the spatula if needed after an initial pass. For a cleaner finish, mask the sides of the joint with tape prior to filling.

## Cure Time

Dymonic 100 generally cures at a rate of 3/32 in. per day at 75° F (24° C) and 50% relative humidity. Dymonic 100 will skin in 2 hours and be tack free in 6-8 hours. The cure time will increase as temperatures and/or humidity decrease. A good rule of thumb is one additional day for every 10° F decrease in temperature.

## Clean up

Excess sealant and smears adjacent to the joint interface can be carefully removed with xylene or mineral spirits before the sealant cures. Any utensils used for tooling can also be cleaned with xylene or mineral spirits.

## Limitations

- Use with adequate ventilation.
- Always utilize the accompanying MSDS for information on Personal Protective Equipment (PPE) and health hazards.

## Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or refund the purchase of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.



# Dymonic<sup>®</sup> FC Standard Colors

MTO/custom colors & alternate packaging available

	
ALMOND	
	
ALUMINUM STONE	
	
ANODIZED ALUMINUM	
	
BEIGE	
	
BLACK	
	
BRONZE	
	
BUFF	
	
DARK BRONZE	
	
GRAY	
	
LIMESTONE	
	
OFF WHITE	
	
REDWOOD TAN	
	
STONE	
	
WHITE	
	
NATURAL CLAY	

This guide only offers a general representation of our color offering. Colors viewed on a computer screen and then printed will vary and will never be an exact representation of the actual pigment. When matching is critical, please refer to our color card or sample color strips.