



EUCLID CHEMICAL

# BARACADE M.E.

## SILICONE MICRO EMULSION WATER REPELLENT

### DESCRIPTION

**BARACADE M.E.** is an oligomeric alkyl alkoxy siloxane concentrate. When diluted with water, BARACADE M.E. self-emulsifies into a unique product capable of repelling water on concrete or masonry surfaces. BARACADE M.E. is a breathable, non-staining, colorless material which penetrates deep into the surface to seal out moisture, reduce efflorescence and minimize the damaging effects of freeze-thaw cycles. BARACADE M.E. protects without altering the appearance or texture of the treated surface and improves resistance to airborne dirt, smog and other air pollutants.

### PRIMARY APPLICATIONS

BARACADE M.E./9 is mixed 9 parts water to 1 part BARACADE M.E. for vertical applications such as:

- Precast & prestressed
- Above grade
- Exposed aggregate
- Poured-in-place
- Concrete block

BARACADE M.E./4.5 is mixed 4.5 parts water to 1 part BARACADE M.E. for horizontal applications such as:

- Sidewalks
- Ramps
- Parking decks
- Bridge decks
- Industrial floors

### TECHNICAL INFORMATION

#### Material Properties\* @ 75°F (25°C)

#### Baracade M.E. Test Results NCHRP 244 Series II Tests

	Minimum Requirement	BARACADE M.E./4.5
<b>Reduction in water absorption</b>	75%	80%
<b>Water vapor transmission</b>	100%	121%
<b>Reduction in chloride ion intrusion</b>	75%	83%
<b>California Test Method (Cal trans)</b>		
<b>Water absorption, 24 hours</b>	1% max	0.65%
<b>Freeze thaw cycles</b>	200 max	433
<b>VOC content, ASTM D 3960</b>	400 max	349 g/L

**Flash point of concentrate** 77°F

**Flash point after dilution** None

#### Solids by weight (after dilution)

BARACADE M.E./9	10%
BARACADE M.E./4.5	18%

**Appearance of Liquid** pale yellow

**Appearance when dry** clear

**Resistance to UV** excellent

**Abrasion Resistance** excellent

**Water permeance** ASTM E 514

BARACADE M.E./9 passes

\* Values presented are typical and are not necessarily referenced to create specifications.

### PACKAGING

BARACADE M.E. is packaged in 55 gal (208 L) drums, 5 gal (18.9 L) pails and 1 gal (3.8 L) units.

### SHELF LIFE

1 year in original, unopened container

### COVERAGE

Because of variations in surface density, the following coverage rates are approximate and are intended for estimating purposes only. Use test applications on actual surfaces to accurately determine coverage rates. Extremely porous surfaces may require two coats.

#### Vertical Applications

Surface Type	# of Coats	BARACADE M.E./9		ft <sup>2</sup> /gal (m <sup>2</sup> /L)	
		1st Coat	2nd Coat	1st Coat	2nd Coat
Poured and Precast Concrete	1	120 to 170 (2.9 to 4.2)	-		
Slump Block	1	70 to 80 (1.7 to 2.0)	-		
Brick and Stucco	1	80 to 125 (2.0 to 3.1)	-		
Plaster and Stone/Tile	1	200 to 300 (4.9 to 7.4)	-		
Standard Block ASTM C 90 Grade N Type I)	2	40 to 80 (0.98 to 2.0)	60 to 120 (1.5 to 2.9)		
Split Faced Block	2	40 to 80 (0.98 to 2.0)	60 to 120 (1.5 to 2.9)		

#### Horizontal Applications

	BARACADE M.E./4.5	
Concrete	2	100 to 150 (2.4 to 3.7)

## DIRECTIONS FOR USE

**Surface Preparation:** Cure new concrete 28 days before application. Surface must be clean, dry, structurally sound, free of curing or form release compounds, and other contaminants that will prevent the proper penetration of BARACADE M.E.. Prior to application, joints or cracks in movement must be properly sealed with an elastomeric joint sealant. Non-moving cracks or voids wider than 1/64 inch (0.4 mm) must be filled with a suitable patching material. Do not apply BARACADE M.E. to a wet surface. Surfaces must dry a minimum of 24 hours following rain or other moisture. Install caulking before BARACADE M.E. application. Mask or protect adjacent surfaces, including grass, plants, shrubs, glass, rubber, and asphalt from overspray or drips.

**Mixing:** BARACADE M.E. is supplied in a concentrated form and must be mixed with clean, potable water immediately before application. Prepared solutions must be applied within 12 hours of mixing.

**Vertical Surfaces:** BARACADE M.E./9 has a 9:1 mix ratio. (9 gal (34 L) water to 1 gal (3.8 L) BARACADE M.E.)

**Horizontal Surfaces:** BARACADE M.E./4.5, has a 4.5:1 mix ratio. (4.5 gal (17 L) water to 1 gal (3.8 L) BARACADE M.E.) **Special Conditions:** For extremely dense, porous, or surfaces to be painted, contact your local Euclid Chemical representative.

**Equipment:** BARACADE M.E. should be applied with low pressure airless spray equipment using no more than 15 to 20 psi (0.103 to 0.138 MPa) air pressure. For proper application to most porous substrates, use spray tips with an orifice size no smaller than 0.035 inch (0.9 mm). Some dense vertical surfaces may require smaller orifice sizes to prevent sags and run downs.

**Application:** Each coat consists of a light fog spray followed immediately with a flood coat. The fog spray wets the surface to break the surface tension and allows the flood coat to deeply penetrate the surface. The flood coat must be applied before the fog coat dries.

**Dense Vertical Surfaces:** On precast concrete and other dense surfaces, apply BARACADE M.E. in several fog coats to the point of saturation with no "run down". Roll out excess material to prevent surface build-up and curtaining.

**Porous Vertical Surfaces:** Spray a fog coat and follow immediately with the flood coat of BARACADE M.E. applied with uniform, overlapping, horizontal strokes. Use sufficient material for saturation and to cause an 8 to 10 inch (20.3 to 25.4 cm) rundown from the point of contact. Fully saturate mortar joints. One coat of material is generally sufficient, but very porous surfaces such as normal weight concrete block may require two coats. Excess material that remains on the surface may result in a glossy or discolored appearance.

**Horizontal Surfaces:** Apply two coats of BARACADE M.E. in a uniform coat "wet on wet basis" to the point of saturation. Do not apply more material than can be absorbed into the surface within 10 seconds. Remove excess material with a squeegee or paint roller.

## CLEAN-UP

Clean drips, runs and overspray residue while still wet, with detergent and water. Dried material may require solvent for removal. Clean application and spray equipment with detergent and water immediately following use.

## PRECAUTIONS/LIMITATIONS

- Do not overdilute BARACADE M.E.
- Do not apply BARACADE M.E. to frozen or frost filled surfaces, or when the ambient or surface temperature falls below 40°F (4°C).
- Do not apply BARACADE M.E. to surfaces warmer than 95°F (35°C).
- Store between 40°F to 85°F (4°C to 29°C).
- Do not apply BARACADE M.E. if rain is forecast within 12 hours.
- Do not apply BARACADE M.E. to non-absorbent materials such as glass, metal, glazed brick, or glazed tile.
- Do not allow BARACADE M.E. to puddle. All product should penetrate the substrate with no surface build-up.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.14

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.