



CITRIC ACID RAPID REPAIR RETARDER

Citric Acid Rapid Repair Retarder is a powdered additive to increase the setting time of our Rapid Repair products. It is available in bulk lots and small individual packets. The dry Rapid Repair Retarder powder should be mixed into the mixing water first. One packet of Rapid Repair Retarder will extend the setting time of a bag of Rapid Repair material for approximately 15 to 30 minutes at normal temperatures 24°C (75°F).

Rapid Repair Retarder acts as a water-reducing agent and improves fluidity. Concrete strength is improved by about 5%.

TECHNICAL DATA:

Typical Properties

Appearance	White Crystalline Powder
Bulk density, Kg/m ³	1665
PH (25°C in 5% solution)	1.8

RECOMMEND DOSAGE:

1 packet per bag of Rapid Repair material

Notice to User - Con-Spec Industries Ltd. warrants that the product described on the face hereof has been manufactured of selected raw materials by skilled technicians. Con-Spec Industries Ltd. shall not be responsible for any claims resulting from the failure to utilize the product in the manner in which it was intended and in accordance with instructions provided for use of product. The only obligation of Con-Spec Industries Ltd. shall be to replace any quantity of this product which proved to be defective. Con-Spec Industries Ltd. assumes no liability, loss, or damage resulting from use of this product. Your use of this product constitutes your acknowledgment and acceptance of these terms and limitations.